

# JT 8500 WG - PT, PG BF, RG BF, RG

#### PRODUCT DESCRIPTION

Budget monomeric calendered self-adhesive printing media

# Face material:

90 µm white gloss PVC

#### Adhesive:

**JT 8500 WG - PT:** Emulsion acrylic permanent transparent

JT 8500 WG - PG BF: Emulsion acrylic permanent grey bubble free

JT 8500 WG - RG BF: Emulsion acrylic removable arev bubble free

JT 8500 WG - RG: Emulsion acrylic removable grey

#### Liner:

**JT 8500 WG-PG BF/RG BF/PT/RG:** 140 g/sqm 2-sided PE coated paper

#### **TYPICAL USE**

Short -term indoor and outdoor promotional graphics on flat smooth surfaces.

#### **PROCESSING**

Especially designed for solvent based, eco-solvent, mild solvent, Latex and UV inkjet printing on wide-format printing equipment.

To achieve optimal protection and durability, JT 8500 Series needs to be laminated with LF 8500 Series.

To achieve the best possible print quality, please make sure that the correct ICC profiles or printer settings are used.

Profiles can be obtained from our subsidiaries or distributors, or can be downloaded from: www.mactacgraphics.eu.

For further information on printing and laminating, please refer to TB 4.1 "Guidelines on handling, converting and applying Mactac Digital media."

# **SHELF LIFE**

2 years when stored at +15 to  $25^{\circ}$ C and  $\pm$  50 % relative humidity (in the original packaging).

## **APPLICATION METHOD**

Mactac Digital media must be applied following the instructions in TB 4.1 "Guidelines on handling, converting and applying Mactac Digital media", available from the resource section at

# www.mactacgraphics.eu.

To ensure application suitability, always test the proposed construction under actual application and end-use conditions before going into full production.

## PHYSICAL PROPERTIES (TYPICAL VALUES)

Adhesive data, 23°C (N/25 mm)	Average values	Test method		
Quick tack on glass JT 8500 WG- PT: JT 8500 WG- PG BF: JT 8500 WG- RG BF: JT 8500 WG- RG:	12 N/A N/A 4	FTM 9		
Peel 24 hours on glass JT 8500 WG- PT: JT 8500 WG- PG BF: JT 8500 WG- RG BF: JT 8500 WG- RG:	14 15 8 3	FTM 1		
Dimensional stability				
Shrinkage (48 hours at 70°C applied on aluminium)	Max. 1.0 mm	FTM 14		

### Temperature ranges

Minimum application temperature	+ 10°C
Service temperature range of use	- 20°C to + 70°C

## Certifications

Fire certification	B-s1, d0	EN 13501-1
JT 8500 WG- PT & RG		

# **EXPECTED DURABILITY\***

Central Europe Zone 1

Unprocessed	3 years	ISO 4892-2.
Printed & laminated	2 years	ISO 4892-2.

\*For more information, refer to Technical Bulletin 7.5: "Outdoor Durability of combined MACtac print media and laminates".

Note: Overlamination of the inkjet-printed material delays the eventual colour fading that may occur over time. This colour fading is dependent on the quality of the inkjet inks, the orientation of the printed material, the angle of display and the exact geographical location of exposure.

Exposure to severe temperatures, ultraviolet light, and/or conditions in Southern European countries, tropical, sub-tropical or desert regions will cause more rapid deterioration. This also applies to polluted areas, high altitudes and south-facing exposure. No durability warranty is given for horizontal exposure.

## DISCLAIMER

All Mactac statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Mactac products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purposes. All Mactac's products are sold subject to Mactac's general terms and conditions of sale, see http://terms.europe.averydennison.com



Email: contact.mactac@mactac.eu Website: www.mactacgraphics.eu

