

Avery Dennison® MPI 2126 Hi-Tack Easy Apply™ Matte White Premium Calendered Vinyl Hi-Tack Easy Apply™

Features

- Excellent printability on eco-solvent, solvent, latex and UV curable inkjet printers
- Easy Apply™ adhesive system with air egress channels for fast bubble and wrinkle free application
- StaFlat™ liner provides easy handling and converting properties
- Matte finish for superior low glare appearance
- Excellent adhesion to low surface energy and difficult to adhere to Substrates such as plastics and painted metal surfaces
- Very good low temperature adhesive performance
- Good conformability to flat and simple curved surfaces
- Very good dimensional stability after installation
- Excellent outdoor durability and performance

Conversion+

- | | |
|--|---|
| <input checked="" type="checkbox"/> Flat bed cutters | <input type="checkbox"/> Cold overlaminating |
| <input type="checkbox"/> Friction fed cutters | <input type="checkbox"/> Electrostatic printing |
| <input checked="" type="checkbox"/> Die cutting | <input checked="" type="checkbox"/> Latex inkjet |
| <input checked="" type="checkbox"/> Thermal transfer | <input checked="" type="checkbox"/> Eco solvent inkjet |
| <input checked="" type="checkbox"/> Screen printing | <input checked="" type="checkbox"/> Solvent inkjet |
| <input type="checkbox"/> Offset printing | <input checked="" type="checkbox"/> UV curable inkjet |

*Always test with your combination of printer and ink prior to commercial use.

Application

- Avery Dennison recommends a maximum total ink limit of 250% with solvent inkjet printing to ensure optimal performance.
- Refer to Instructional Bulletins 1.01, 1.4, 4.06 & 4.14 for printing, laminating and application instructions.

Uses

Avery Dennison MPI 2126 Hi Tack Easy Apply™ matte premium calendared film is designed for use in demanding applications. For use on low surface energy substrates such as plastics, powder coat paints, fiberglass, clear coats and painted metal surfaces.

Description



Film: 80 micron matte white polymeric calendared vinyl



Adhesive: Clear high tack, permanent acrylic with Easy Apply™, designed for low surface energy substrates



Backing: Two side PE coated StaFlat™ paper, 145g/m²



Outdoor life: Up to 6 years (unprinted)

Application surface: Flat, simple curves, gentle corrugations

Common Applications

- Indoor applications
- Slightly structured surfaces
- Low surface energy substrates
- Heavy Equipment
- Truck and Trailers
- Buses and Transit
- Recreational Vehicles

Physical characteristics

General

Calliper, face film	ISO 534	86 micron
Calliper, face film & adhesive	ISO 534	111 micron
Dimensional stability	DIN 30646	0.89 mm max
Elongation	ISO 527 (Unprinted film)	100% min
Gloss	Hunter Gloss @ 60°	<16
Adhesion, ultimate (24 hrs)	LSE - Plastics	718 N/m
	LSE - Clear coats	753 N/m
	LSE - Paints	788 N/m
	LSE - Textured Substrates	613 N/m
	Stainless Steel	963 N/m
	(LSE - Low Surface Energy)	
Flammability		Self extinguishing
Shelf life	Stored at 22° C/50-55 % RH	2 years
Accelerated ageing	DIN 53387 1000 hours exposure	No negative impact on film performance
Durability **	Vertical exposure	Up to 6 years (unprinted)
		Up to 4 years (printed) ^

^ See ICS Performance Guarantee Durability Bulletin for your specific printer and ink combination for further information

Thermal

Application temperature	Minimum: + 5°C
Temperature range	- 40°C to + 80°C

Chemical

Resistant to most petroleum based oils, greases and aliphatic solvents

Resistant to most mild acids, alkalies and salts

Note:

Materials which have been solvent inkjet printed must be properly dried and cured before further processing, like laminating, varnishing, trimming, contour cutting or application. The residual solvents can otherwise change the products' specific features and properties.

Test Methods

Dimensional stability:

Is measured on a 150 x 150 mm aluminium panel to which a specimen has been applied; 72 hours after application the panel is exposed for 48 hours to + 70°C, after which the shrinkage is measured.

Adhesion:

(FTM-1, FINAT) is measured by peeling a specimen at a 180° angle from a stainless steel or float glass panel, 24 hours after the specimen has been applied under standardised conditions. Initial adhesion is measured 20 minutes after application of the specimen.

Flammability:

A specimen applied to aluminium is subjected to the flame of a gas burner for 15 seconds. The film should stop burning within 15 seconds after removal from the flame.

Temperature range:

A specimen applied to stainless steel is exposed at high and low temperatures and brought back to room temperature. 1 hour after exposure the specimen is examined for any deterioration. Note: Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids, dyes, etc. may eventually cause deterioration.

Important

Information on physical characteristics is based upon tests we believe to be reliable. The values listed herein are typical values and are not for use in specifications. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of any material for their specific use.

All technical data is subject to change without prior notice.

Warranty

Avery® materials are manufactured under careful quality control and are warranted to be free from defect in material and workmanship. Any material shown to our satisfaction to be defective at the time of sale will be replaced without charge. Our aggregate liability to the purchaser shall in no circumstances exceed the cost of the defective materials supplied. No salesman, representative or agent is authorised to give guarantee, warranty, or make any representation contrary to the foregoing.

All Avery® materials are sold subject to the above conditions, being part of our standard conditions of sale, a copy of which is available on request.

**Durability

Durability is based on exposure conditions in the normal middle European and central North American regions (Zone 1). Actual performance life will depend on substrate preparation, exposure conditions and maintenance of the marking. For instance, in the case of signs facing north in the southern hemisphere or south in the northern hemisphere; in areas of long high temperature exposure such as northern Australia; in industrially polluted areas or high altitudes, exterior performance will be decreased. Please refer to Avery Dennison Instructional Bulletin 1.3 for definitions and reductions based on the 'Zone System'.

†Compatible with most media and ink combinations. Test prior to use.

***Information unavailable at time of printing.

Chemical Resistance:

All chemical tests are conducted with test panels to which a specimen has been applied. 72 hours after application the panels are immersed in the test fluid for the given test period. 1 hour after removing the panel from the fluid, the specimen is examined for any deterioration.

Corrosion Resistance:

A specimen applied to aluminium is exposed to saline mist (5% salt) at 35°C. After exposure, the film is removed and the panel is examined for traces of corrosion.